

Lendell Parapet HH-1000L PMMA, Heat Resistant

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, Heat Resistant, Molded

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lendell-Parapet-HH-1000L-PMMA-Heat-Resistant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	ASTM D792
Water Absorption	0.30 %	0.30 %	ASTM D570
Linear Mold Shrinkage	0.0020 - 0.0060 cm/cm	0.0020 - 0.0060 in/in	ASTM D955
Melt Index of Compound	2.1 g/10 min @Load 3.80 kg, Temperature 230 Â°C	2.1 g/10 min @Load 8.38 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	105	105	ASTM D785
Tensile Strength, Yield	75.5 MPa	11000 psi	ASTM D638
Elongation at Yield	7.0 %	7.0 %	ASTM D638
Flexural Yield Strength	122 MPa	17600 psi	ASTM D790
Flexural Modulus	3.43 GPa	498 ksi	ASTM D790
Izod Impact, Notched	0.157 J/cm	0.294 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	97.0 Â°C	207 Â°F	unannealed; ASTM D648
	106 Â°C	223 Â°F	annealed; ASTM D648
Vicat Softening Point	118 Â°C	244 Â°F	ASTM D1525
Flammability, UL94	HB	HB	

Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ASTM D542
Haze	0.30 %	0.30 %	ASTM D1003
Transmission, Visible	93 %	93 %	ASTM D1003

Optical Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China