

## Loctite® 460 Low odor/low bloom Alkoxy Cyanoacrylate Bonding Adhesive

Category : Polymer , Adhesive , Thermoset , Acrylic/Cyanoacrylate Adhesive

**Material Notes:**

Cyanoacrylate Bonding Adhesives Loctite® technology has made the productivity promises of cyanoacrylate adhesives a reality with the industry's widest selection of high-performance, application-specific, instant adhesives. Loctite® Instant Adhesives are available in a variety of viscosities, cure speeds, gap-filling capability and substrate compatibility. The ultra high-performance PRISM® family offers additional products that surpass the most stringent demands, including toughened formulations, low odor and low blooming products, surface insensitive and thermally resistant formulations. Loctite® 460 Low odor/low bloom Alkoxy Cyanoacrylate Bonding Adhesive

Bonding Type: Cyanoacrylate Typical Use: Close fitting parts.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Loctite-460-Low-odorlow-bloom-AlkoxyCyanoacrylate-Bonding-Adhesive.php](http://www.lookpolymers.com/polymer_Loctite-460-Low-odorlow-bloom-AlkoxyCyanoacrylate-Bonding-Adhesive.php)

Physical Properties	Metric	English	Comments
Density	1.10 g/cc	0.0397 lb/in <sup>3</sup>	
Viscosity	45 cP	45 cP	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	17.9 MPa	2600 psi	Grit blasted steel

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	71.1 °C	160 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	0.800 min	0.0133 hour	
	1440 min	24.0 hour	Full Cure; Varies with substrates

Descriptive Properties	Value	Comments
Color	Clear	
Gap Fill	0.004 in.	

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China