

Loctite® 5206 Flexible Cure Flange Sealant

Category : Polymer , Adhesive , Thermoset

Material Notes:

Anaerobic Gasketing Loctite® 5206 Flexible Cure Flange Sealant Slow curing allows for micro-movement during assembly operations. Good sealing properties against oil and water/glycol. High viscosity. Recommended Primer: 7649 (N) or 7471 (T). Typical Use: Slow curing, flexible

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loctite-5206-Flexible-CureFlange-Sealant.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	
Viscosity	110000 - 345000 cP	110000 - 345000 cP	Thixotropic

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	5.00 - 1440 min	0.0833 - 24.0 hour	Full Cure
	60.0 - 1440 min	1.00 - 24.0 hour	Full Cure, Unprimed

Descriptive Properties	Value	Comments
Color	Red	
Gap Fill	0.010 in.	Unprimed
	0.02 in.	Primed

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China