

## Loctite® 661 Retaining Compound

Category : Polymer , Adhesive , Thermoset

### Material Notes:

RetainersLoctite Corporation, the pioneer of anaerobic adhesives, has applied this technology to create retaining compounds that increase the shear strength of cylindrical, non-threaded assemblies. Finding wide acceptance as a standard method for assembling press and slip-fitted parts, Loctite® Retaining Compounds fill the "inner space" between components and cure to form a strong precision assembly.

Formulated in a selection of viscosities, gap filling ability, flexibility and strength characteristics, Loctite® Retaining Compounds can be applied with automatic process equipment or dispensed manually.Loctite® 661 Retaining CompoundRecommended Primer: 7471 (T).

Typical Use: Fast anaerobic curing, UV curing for edge fillets

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Loctite-661-Retaining-Compound.php](http://www.lookpolymers.com/polymer_Loctite-661-Retaining-Compound.php)

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0401 lb/in <sup>3</sup>	
Viscosity	500 cP	500 cP	

Mechanical Properties	Metric	English	Comments
Adhesive Bond Strength	24.1 MPa	3500 psi	Steel/Steel; Varies with substrates

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	149 °C	300 °F	
Minimum Service Temperature, Air	-53.9 °C	-65.0 °F	

Processing Properties	Metric	English	Comments
Cure Time	5.00 min	0.0833 hour	
	1440 min	24.0 hour	Full Cure; Steel
	@Temperature 25.0 °C	@Temperature 77.0 °F	

Descriptive Properties	Value	Comments
Color	Amber	
Gap Fill	0.006 in.	Diametral

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China