

Loctite® Durabond® E-20NS Epoxy Adhesive

Category: Polymer, Adhesive, Thermoset, Epoxy, Epoxy Adhesive

Material Notes:

Epoxy AdhesivesLoctite offers a complete line of one-part and two-part epoxy and urethane adhesives for structural bonding, potting and encapsulating. The Loctite® Durabond® line contains 14 application-specific products designed to outperform the competition in all aspects: better adhesion, better flow, less odor, improved clarity, higher strength, and greater durability. All two-part Durabond® Structural Adhesives are packaged in easy-to-use, side-by-side cartridges for use with our manual dispensers and mix nozzles.Loctite® E-20NS Metal bonder, non-sag, high peel, high shear Durabond® Epoxy AdhesiveA metal bonding epoxy with a 20-minute worklife. Light tan, nonsag, high peel, high shear.Mix Ratio by Volume, Resin:Hardener = 2:1 Bonding Type: Epoxy

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loctite-Durabond-E-20NS-Epoxy-Adhesive.php

Physical Properties	Metric	English	Comments
Viscosity	30000 cP	30000 cP	Mixed - high; Resin - nonsag paste; Hardener - 30,000 cP

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	90	90	
Adhesive Bond Strength	13.8 - 27.6 MPa	2000 - 4000 psi	Varies with substrates
Peel Strength	0.877 - 5.26 kN/m	5.00 - 30.0 pli	Varies with substrates.

Thermal Properties	Metric	English	Comments
Glass Transition Temp, Tg	87.0 °C	189 °F	

Electrical Properties	Metric	English	Comments
Dielectric Strength	23.6 kV/mm	600 kV/in	Test run on 1/8" specimens.

Processing Properties	Metric	English	Comments
Pot Life	20 min	20 min	

Descriptive Properties	Value	Comments
Color	Light tan	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com



Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China