

Lord Adhesives 648 Low Odor, Low Flammability, Non Sag, Metal Use Acrylic Adhesive

Category : Polymer , Adhesive , Thermoset

Material Notes:

Lord Adhesives 648 Low Odor, Low Flammability, Non Sag, Metal Use Acrylic Adhesive

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lord-Adhesives-648-Low-Odor-Low-Flammability-Non-Sag-Metal-Use-Acrylic-Adhesive.php

Physical Properties	Metric	English	Comments
Density	1.11 g/cc	0.0403 lb/in ³	
Viscosity	180000 - 300000 cP	180000 - 300000 cP	

Thermal Properties	Metric	English	Comments
Flash Point	46.0 Â°C	115 Â°F	

Processing Properties	Metric	English	Comments
Cure Time	120 min	2.00 hour	
Pot Life	8.0 - 12 min	8.0 - 12 min	Time before parts must be mated

Descriptive Properties	Value	Comments
Color	Off-White	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China