

Lord Adhesives Flocklok® Catalyst 6

Category : Other Engineering Material , Catalyst/Initiator

Material Notes:

Flocklok® adhesive Catalyst 6 is used with moisture curing polyurethanes to accelerate the cure rate. The addition of 1% - 3% Flocklok adhesive Catalyst 6 is suggested. Flocklok adhesive Catalyst 6 is an organic product and is easily dispersed with all Flocklok products. All information provided by Lord.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lord-Adhesives-Flocklok-Catalyst-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.840 - 0.880 g/cc	0.840 - 0.880 g/cc	
Viscosity Measurement	10 - 15	10 - 15	Seconds; 4mm DIN cup

Thermal Properties	Metric	English	Comments
Flash Point	17.0 Â°C	62.6 Â°F	Seta

Processing Properties	Metric	English	Comments
Shelf Life	24.0 Month	24.0 Month	
	@Temperature 21.0 - 27.0 Â°C	@Temperature 69.8 - 80.6 Â°F	

Descriptive Properties	Value	Comments
Appearance	Transparent	
Composition	Tin organic dissolved in xylene/ketone mixture	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China