

Lotte Chemical Titan TITANLENE® LDF268GG Low density polyethylene

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Extrusion Grade

Material Notes:

LDF268GG is a low density polyethylene resin for film extrusion. LDF268GG has medium slip and anti-block additives. LDF268GG meets the U.S. Food and Drug Administration (FDA) criteria for food contact use as specified in 21 CFR 177.1520 (c) 2.1 & (c) 2.2. Applications: High clarity thin film Food wrap Diaper backing Textile packaging Additives: Medium slip Antiblock Advantages: Excellent transparency Good drawdown Excellent process ability Information provided by Titan Chemicals

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lotte-Chemical-Titan-TITANLENE-LDF268GG-Low-density-polyethylene.php

Physical Properties	Metric	English	Comments
Base Resin Density	0.922 g/cc	0.0333 lb/in ³	ASTM D1505
Thickness	30.0 microns	1.18 mil	extruded at 2.5:1 BUR
Base Resin Melt Index	5.0 g/10 min	5.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Film Elongation at Break, MD	250 %	250 %	ASTM D882
Film Elongation at Break, TD	440 %	440 %	ASTM D882
Elmendorf Tear Strength, MD	9.50 g/micron	241 g/mil	ASTM D1922
Elmendorf Tear Strength, TD	4.00 g/micron	102 g/mil	ASTM D1922
Dart Drop	2.50 g/micron	63.5 g/mil	ASTM D1709
Film Tensile Strength at Break, MD	19.6 MPa	2840 psi	ASTM D882
Film Tensile Strength at Break, TD	17.7 MPa	2570 psi	ASTM D882
1% Secant Modulus, MD	215.74 MPa	31291 psi	ASTM D882
1% Secant Modulus, TD	245.16 MPa	35558 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	93.0 Å°C	199 Å°F	resin; ASTM D1525

Optical Properties	Metric	English	Comments
Haze	5.0 %	5.0 %	ASTM D1003

Processing Properties	Metric	English	Comments
-----------------------	--------	---------	----------

Melt Temperature Processing Properties	160 - 180 A°C Metric	320 - 356 A°F English	Comments
Blow-up Ratio (BUR)	2.5	2.5	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China