

## Loxim 220 12HB Polybutylene Terephthalate

Category : Polymer , Thermoplastic , Polyester, TP , Polybutylene Terephthalate (PBT) , Polybutylene Terephthalate (PBT), 20% Glass Fiber Filled

**Material Notes:**

Information provided by Loxim Industries

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Loxim-220-12HB-Polybutylene-Terephthalate.php](http://www.lookpolymers.com/polymer_Loxim-220-12HB-Polybutylene-Terephthalate.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.45 g/cc	1.45 g/cc	ASTM D792
Filler Content	20 %	20 %	
Linear Mold Shrinkage	0.0060 - 0.0080 cm/cm	0.0060 - 0.0080 in/in	ASTM D1299

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	ASTM D683
Elongation at Break	3.0 %	3.0 %	ASTM D638
Tensile Modulus	5.50 GPa	798 ksi	ASTM D638
Flexural Modulus	5.50 GPa	798 ksi	ASTM D790
Izod Impact, Notched	0.450 J/cm	0.843 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 - 215 Â°C	410 - 419 Â°F	ASTM D1525, HDT Method B
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China