

Loxim 330 01V0 Nylon 6

Category : Polymer , Thermoplastic , Nylon , Nylon 6 , Nylon 6 , 30% Glass Fiber Filled , Nylon 6, Glass Fiber Filled, Flame Retardant

Material Notes:

Information provided by Loxim Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loxim-330-01V0-Nylon-6.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.55 g/cc	1.55 g/cc	ASTM D792
Linear Mold Shrinkage	0.0030 cm/cm	0.0030 in/in	ASTM D1299

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	150 MPa	21800 psi	ASTM D683
Elongation at Break	2.0 - 3.0 %	2.0 - 3.0 %	ASTM D638
Flexural Modulus	7.50 GPa	1090 ksi	ASTM D790
Izod Impact, Notched	0.900 - 1.00 J/cm	1.69 - 1.87 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	210 Â°C	410 Â°F	ASTM D1525, HDT Method B
Flammability, UL94	V-0 @Thickness 1.60 mm	V-0 @Thickness 0.0630 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China