

Loxim 841 02T HB Polypropylene Compound, 40% Talc Filled, Flame Retardant

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Talc Filler , Polypropylene, Flame Retardant

Material Notes:

Information provided by Loxim Industries

Order this product through the following link:

http://www.lookpolymers.com/polymer_Loxim-841-02T-HB-Polypropylene-Compound-40-Talc-Filled-Flame-Retardant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 - 1.20 g/cc	1.10 - 1.20 g/cc	ASTM D792
Filler Content	40 %	40 %	
Linear Mold Shrinkage	0.010 - 0.012 cm/cm	0.010 - 0.012 in/in	ASTM D1299

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	24.0 - 26.0 MPa	3480 - 3770 psi	ASTM D683
Flexural Modulus	2.60 - 2.80 GPa	377 - 406 ksi	ASTM D790
Izod Impact, Notched	0.400 - 0.600 J/cm	0.749 - 1.12 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	115 - 120 Å°C	239 - 248 Å°F	ASTM D1525, HDT Method B
Flammability, UL94	HB @Thickness 1.60 mm	HB @Thickness 0.0630 in	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China