

Lubriplate SYN SYN-1602 PAO-Based Multi-Purpose Grease

Category: Fluid, Lubricant, Lithium Gellant, Polyalphaolefin (PAO)

Material Notes:

Manufactured with 100% PAO base fluids and thickened with lithium complex for superior oxidation stability, better wear protection, and significantly better operating temperature ranges. Fortified with additives to prevent rust and corrosion, as well as reduce grease bleed.

Applications: Multi-purpose, heavy-duty applications. SYN-1600 Series Greases are available in Pails, 1/4 Drums & Drums. SYN-1601 & SYN-1602 are also available in Cartridges. Information provided by Lubriplate

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubriplate-SYN-SYN-1602-PAO-Based-Multi-Purpose-Grease.php

| Physical Properties | Metric | English | Comments |
|-------------------------------------|----------|----------|----------|
| Saybolt Viscosity at 100°F | 2066 SUS | 2066 SUS | |
| Kinematic Viscosity at 40°C (104°F) | 446 cSt | 446 cSt | |

| Mechanical Properties | Metric | English | Comments | |
|----------------------------|--------|---------|------------------------|--|
| Penetration P(0), 1/10 mm | 265 | 265 | Unknown Amount of Work | |
| Penetration P(60), 1/10 mm | 295 | 295 | Unknown Amount of Work | |

| Thermal Properties | Metric | English | Comments | |
|----------------------------------|----------|----------|-------------------|--|
| Minimum Service Temperature, Air | -42.8 °C | -45.0 °F | Approx. Cold test | |
| Dropping Point | 260 °C | 500 °F | ASTM Test | |

| Descriptive Properties | Value | Comments |
|--------------------------------------|-------|----------|
| Antiwear (AW)/ Extreme Pressure (EP) | AW/EP | |
| NLGI Grade | 2 | |
| Rust/Oxidative Additives | YES | |
| Water Resistant | YES | |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058 Skype: lookpolymers



Address: United North Road 215, Fengxian District, Shanghai City, China