

Lubrizol Advanced Materials PEARLBOND® 100 Linear Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Pearlbond®, 100 is a linear, polycaprolactone-based polyurethane, supplied in form of small white granules, which combines a very high crystallization rate with a very high thermoplasticity level. It is used for Hot Melt adhesives. Application: Pearlbond®, 100 is mainly used for making heat-sealable fabrics (thermobonding), obtained by coating processes such as scattering or dot-coating (powder or paste). In all cases, the product is previously ground into powder, by cryogenic grinding. The particle size of the powder will depend on the application technique to be used.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-PEARLBOND-100-Linear-Thermoplastic-Polyurethane.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 2781
Viscosity	700000 cP @Temperature 160 °C	700000 cP @Temperature 320 °F	Melt viscosity @ 2.16 kg; ISO 1133
Melt Flow	15 - 30 g/10 min @Load 2.16 kg, Temperature 170 °C	15 - 30 g/10 min @Load 4.76 lb, Temperature 338 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	51	51	ISO 868

Thermal Properties	Metric	English	Comments
Melting Point	64.0 - 68.0 °C	147 - 154 °F	MQSA 70 A
Softening Point	55.0 - 60.0 °C	131 - 140 °F	MQSA 70 A

Descriptive Properties	Value	Comments
Crystallization rate (minutes)	Very high	MQSA 12 B
Thermoplasticity	Very high	MQSA 68 A

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China