Lubrizol Advanced Materials PEARLBOND® 101 Linear Thermoplastic Polyurethane

Category : Polymer, Thermoplastic, Polyurethane, TP

Material Notes:

Pearlbondâ, ¢ 101 is a linear, polycaprolactone-based polyurethane, supplied in form of small white granules, which combines a very high crystallization rate with a very high thermoplasticity level. It is used for Hot Melt adhesives. Application: Pearlbondâ, ¢ 101 is mainly used for making heat-sealable fabrics (thermobonding), obtained by coating processes such as scattering or dot-coating (powder or paste). In all cases, the product is previously ground into powder, by cryogenic grinding. The particle size of the powder will depend on the application technique to be used. Pearlbondâ, ¢ 101 is used for textile coating for making shoe-stiffeners (toe puffs & counters), by extrusion or sintering process.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-PEARLBOND-101-Linear-Thermoplastic-Polyurethane.php

| Physical Properties | Metric | English | Comments |
|---------------------|--------------------------------------|--------------------------------------|------------------------------------|
| Density | 1.19 g/cc | 0.0430 lb/in³ | ISO 2781 |
| Viscosity | 380000 cP | 380000 cP | Melt viscosity @ 2.16 kg; ISO 1133 |
| | @Temperature 160 °C | @Temperature 320 °F | |
| Melt Flow | 30 - 60 g/10 min | 30 - 60 g/10 min | ISO 1133 |
| | @Load 2.16 kg, Temperature 170 °C | @Load 4.76 lb, Temperature 338 °F | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|--------|---------|----------|
| Hardness, Shore D | 51 | 51 | ISO 868 |

| Thermal Properties | Metric | English | Comments |
|--------------------|----------------|--------------|-----------|
| Melting Point | 63.0 - 67.0 °C | 145 - 153 °F | MQSA 70 A |
| Softening Point | 55.0 - 60.0 °C | 131 - 140 °F | MQSA 70 A |

| Descriptive Properties | Value | Comments |
|--------------------------------|-----------|-----------|
| Crystallization rate (minutes) | Very high | MQSA 12 B |
| Thermoplasticity | Very high | MQSA 68 A |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com



Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China