

## Lubrizol Advanced Materials PEARLBOND<sup>®</sup> 500 Linear Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

### Material Notes:

Pearlbond<sup>®</sup> 500 is a linear, polycaprolactone-copolyester polyurethane, supplied in form of white spherical granules with a high crystallization rate and a very high thermoplasticity level. Application: Pearlbond<sup>®</sup> 500 can be added to formulations of REACTIVE POLYURETHANE HOT-MELTS (HMPUR), in order to improve the crystallisation speed.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-Advanced-Materials-PEARLBOND-500-Linear-Thermoplastic-Polyurethane.php](http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-PEARLBOND-500-Linear-Thermoplastic-Polyurethane.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ISO 2781
Viscosity	1.57e+6 cP @Temperature 130 °C	1.57e+6 cP @Temperature 266 °F	Melt; ISO 1133
Melt Flow	15 - 30 g/10 min @Load 2.16 kg, Temperature 170 °C	15 - 30 g/10 min @Load 4.76 lb, Temperature 338 °F	ISO 1133

Thermal Properties	Metric	English	Comments
Melting Point	64.0 - 68.0 °C	147 - 154 °F	MQSA 70 A

Chemical Properties	Metric	English	Comments
Total Base Number	<= 3.0	<= 3.0	mg KOH/g; MQSA 47 A

Processing Properties	Metric	English	Comments
Moisture Content	<= 0.15 %	<= 0.15 %	MQSA 44

Descriptive Properties	Value	Comments
Crystallization rate (minutes)	15 - 17	MQSA 12 B
Supply Form	Small white pellets	
Thermoplasticity	Very high	MQSA 68 A

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**