

Lubrizol Advanced Materials PEARLCOAT® 163K Thermoplastic Polyurethane Elastomer

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyether Grade

Material Notes:

PEARLCOAT® 163K is a polyether based TPU, supplied in form of translucent, colorless pellets, combining hardness with excellent low temperature flexibility and very good hydrolysis resistance. PEARLCOAT® 163K is used in melt coatings on textile substrates, for end-uses in industrial coatings (for life-jackets, etc.) obtained by extrusion and calendering. All information provided by Merquinsa

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-PEARLCOAT-163K-Thermoplastic-Polyurethane-Elastomer.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.12 g/cc	1.12 g/cc	ASTM D792
Melt Flow	10 g/10 min @Load 21.6 kg	10 g/10 min @Load 47.6 lb	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	ASTM D2240
Tensile Strength, Yield	30.05 MPa	4359 psi	ASTM D412
Elongation at Break	440 %	440 %	ASTM D412
100% Modulus	0.00601 GPa	0.872 ksi	ASTM D412
300% Modulus	0.01003 GPa	1.455 ksi	ASTM D412
Abrasion	25	25	loss (mm ³); DIN 53.516

Thermal Properties	Metric	English	Comments
Melting Point	166 - 174 Â°C	330 - 345 Â°F	MQSA 111
Softening Point	154 - 166 Â°C	310 - 330 Â°F	film 300Âµm; MQSA 70 (KÃ¶fler)
Glass Transition Temp, Tg	-50.0 Â°C	-58.0 Â°F	DSC, 10Â°C/min; DIN 51.007

Processing Properties	Metric	English	Comments
Zone 1	149 - 160 Â°C	300 - 320 Â°F	
Zone 2	160 - 171 Â°C	320 - 340 Â°F	
Zone 3	170 - 179 Â°C	338 - 355 Â°F	
Zone 4	174 - 185 Â°C	345 - 365 Â°F	

Processing Properties	Metric	English	Comments
Die Temperature	174 - 185 A°C	343 - 365 A°F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China