

## Lubrizol Advanced Materials Pearlstick® 45-40/19 Polycaprolactone based TPU

Category : Polymer , Thermoplastic , Polyurethane, TP

### Material Notes:

Pearlstick® 45-40/19 is an elastic, linear, aromatic polyurethane, supplied in form of white spherical granules with a very high crystallization rate and a medium thermoplasticity level. Solubility: Pearlstick® 45-40/19 is soluble in Acetone, Methyl Ethyl Ketone (MEK), Cyclohexanone, Dimethyl formamide, (DMF), Tetrahydrofuran (THF). Diluting solvents such as Toluene and Ethyl Acetate can be added. The solvents and diluents should be water-free (max. 0.1%), so as to avoid subsequent side reactions during crosslinking with isocyanate. Pearlstick® 45-40/19 should be dissolved in closed tanks and the use of a variable speed agitator is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios. Applications: Pearlstick® 45-40/19 is used for the production of adhesives for bonding plasticized PVC to plasticized PVC or other materials such as leather, textiles, etc. Pearlstick® 45-40/19 has good resistance to temperature, although the addition of a polyfunctional isocyanate improves the heat-resistance still further. Information provided by Merquinsa

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-Advanced-Materials-Pearlstick-45-4019-Polycaprolactone-based-TPU.php](http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-Pearlstick-45-4019-Polycaprolactone-based-TPU.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ISO 2781
Brookfield Viscosity	1700 - 2100 cP	1700 - 2100 cP	Brookfield RVF sp 4, 20 rpm, Solution 15% MEK (MQSA N° 55 A); MQSA 40A

Processing Properties	Metric	English	Comments
Processing Temperature	45.0 °C	113 °F	Min. Activation Temp; EN 12961

Descriptive Properties	Value	Comments
Crystallization Rate (MQSA n° 12 A)	VERY HIGH	
Hydrolysis Resistance	Good	MQSA 34B
Hydroxyl Number	0.1%	MQSA 47A
Solubility - Acetone / Ethyl Acetate	60:40	
Solubility - Acetone / Toluene	60:40	
Solubility - MEK / Toluene	80:20	
Solubility - MEK/ Ethyl Acetate	70:30	
Thermoplasticity Range (MQSA n° 58)	MEDIUM	

Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China