

## Lubrizol Advanced Materials Pearlstick® 45-90/06 Polycaprolactone based TPU

Category : Polymer , Thermoplastic , Polyurethane, TP

### Material Notes:

Pearlstick® 45-90/06 is an elastic, linear, aromatic polyurethane, supplied in form of white spherical granules with a small amount of anti-adherent in the formulation. It has a low crystallization rate and a low thermoplasticity level. Solubility: Pearlstick® 45-90/06 is soluble in Acetone, Methyl Ethyl Ketone (MEK), Cyclohexanone, Dimethyl Formamide, and Tetrahydrofuran (THF). The solvents and diluents should be water-free (max. 0.1 %), so as to avoid subsequent side reactions during crosslinking with isocyanate. It should be dissolved in closed tanks, and the use of a variable speed agitator is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios Applications: Pearlstick® 45-90/06 is used for the production of adhesives for different kinds of materials such as leather, textiles, rubber and a variety of plastics (plasticized PVC, PU elastomers, etc.). Pearlstick® 45-90/06 enables the production of adhesives with a very long open-time, which can be used as one- or twocomponent adhesives. The addition of a polyfunctional isocyanate to improves the heat-resistance and the strength of the joints. The addition of Pearlstick® 45-90/06 to other different types of Pearlstick® increases their open-times. Information provided by Merquinsa

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-Advanced-Materials-Pearlstick-45-9006-Polycaprolactone-based-TPU.php](http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-Pearlstick-45-9006-Polycaprolactone-based-TPU.php)

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in <sup>3</sup>	ISO 2781
Brookfield Viscosity	450 - 750 cP	450 - 750 cP	Brookfield RVF sp 3, 20 rpm, Solution 15% MEK (MQSA n <sup>o</sup> 55 A); MQSA 40A

Processing Properties	Metric	English	Comments
Processing Temperature	40.0 °C	104 °F	Min. Activation Temp; EN 12961

Descriptive Properties	Value	Comments
Crystallization Rate (MQSA n <sup>o</sup> 12 A)	LOW	
Hydrolysis Resistance	Good	MQSA 34B
Hydroxyl Number	0.1%	MQSA 47A
Solubility - Acetone / Ethyl Acetate	70:30	
Solubility - Acetone / Toluene	50:50	
Solubility - MEK / Toluene	80:20	
Solubility - MEK/ Ethyl Acetate	80:20	
Thermoplasticity Range (MQSA n <sup>o</sup> 58)	LOW	

## **Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**