

Lubrizol Advanced Materials Pearlstick® 45-90/12 Polycaprolactone based TPU

Category : Polymer , Thermoplastic , Polyurethane, TP

Material Notes:

Pearlstick® 45-90/06 is an elastic, linear, aromatic polyurethane, supplied in form of white spherical granules with a small amount of anti-adherent in the formulation. It has a low crystallization rate and a low thermoplasticity level. Solubility: Pearlstick® 45-90/06 is soluble in Acetone, Methyl Ethyl Ketone (MEK), Cyclohexanone, Dimethyl Formamide, and Tetrahydrofuran (THF). The solvents and diluents should be water-free (max. 0.1 %), so as to avoid subsequent side reactions during crosslinking with isocyanate. It should be dissolved in closed tanks, and the use of a variable speed agitator is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios Applications: Pearlstick® 45-90/06 is used for the production of adhesives for different kinds of materials such as leather, textiles, rubber and a variety of plastics (plasticized PVC, PU elastomers, etc.). Pearlstick® 45-90/06 enables the production of adhesives with a very long open-time, which can be used as one- or twocomponent adhesives. The addition of a polyfunctional isocyanate to improves the heat-resistance and the strength of the joints. The addition of Pearlstick® 45-90/06 to other different types of Pearlstick® increases their open-times Information provided by Merquinsa

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-Pearlstick-45-9012-Polycaprolactone-based-TPU.php

Physical Properties	Metric	English	Comments
Density	1.19 g/cc	0.0430 lb/in ³	ISO 2781
Brookfield Viscosity	450 - 750 cP	450 - 750 cP	Brookfield RVF sp 3, 20 rpm, Solution 15% MEK (MQSA n ^o 55 A); ISO 2781

Processing Properties	Metric	English	Comments
Processing Temperature	40.0 Å°C	104 Å°F	Min. Activation Temp; EN 12961

Descriptive Properties	Value	Comments
Crystallization Rate (MQSA n ^o 12 A)	LOW	
Hydrolysis Resistance	Good	MQSA 34B
Hydroxyl Number	0.1%	MQSA 47A
Solubility - Acetone / Ethyl Acetate	80:20	
Solubility - Acetone / Toluene	60:40	
Solubility - MEK / Toluene	85:15	
Solubility - MEK/ Ethyl Acetate	85:15	
Thermoplasticity Range (MQSA n ^o 58)	LOW	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China