

## Lubrizol Advanced Materials Pearlstick® D40-70/08 Linear Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP

### Material Notes:

Pearlstick® D40-70/08 is an elastic, linear, aromatic polyurethane, supplied in form of white spherical granules with an extremely high crystallization rate and a very low thermoplasticity level. Solubility: Pearlstick® D40-70/08 is soluble in Acetone, Methyl Ethyl Ketone (MEK), Cyclohexanone, Dimethyl formamide, (DMF), Tetrahydrofurane (THF). Diluting solvents such as Toluene and Ethyl Acetate can be added. The solvents and diluents should be water-free (max. 0.1%), so as to avoid subsequent side reactions during crosslinking with isocyanate. Pearlstick® D40-70/08 gives transparent solutions. It they should be dissolved in closed tanks and the use of high shear equipments is advisable. The final viscosity figures can vary, depending on the stirring process and on the solvent/diluents ratios.

Applications: Pearlstick® D40-70/08 is used for the production of adhesives for bonding plasticized PVC to plasticized PVC or other materials such as leather, textiles, rubber, in the shoe industry. Pearlstick® D40-70/08 enables the production of adhesives with high solids content and low viscosity, which are intended for spray application in the automotive industry and with high performances in the green-strength of the joints and temperature resistance. Information provided by Merquinsa

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-Advanced-Materials-Pearlstick-D40-7008-Linear-Thermoplastic-Polyurethane.php](http://www.lookpolymers.com/polymer_Lubrizol-Advanced-Materials-Pearlstick-D40-7008-Linear-Thermoplastic-Polyurethane.php)

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in <sup>3</sup>	ISO 2781
Brookfield Viscosity	500 - 1100 cP	500 - 1100 cP	Brookfield RVF sp 3, 20 rpm, Solution 15% MEK (MQSA N° 55 A); MQSA 40A

Processing Properties	Metric	English	Comments
Processing Temperature	60.0 Â°C	140 Â°F	EN-12961

Descriptive Properties	Value	Comments
Color	White	
Crystallization Rate	Extremely High	
Heat Resistance	Excellent	MQSA 11F
Hydroxyl Number	0.001	MQSA 47A
Thermoplasticity Level	Very Low	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**