

## Lubrizol ESTANE® 58130 Ester Based Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

### Material Notes:

Features: Fast cycling, broad temperature performance, and durability Use: Injection Molding. Available in Americas, Europe, Middle East, Africa, India and Asia Information provided by Lubrizol

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-58130-Ester-Based-Thermoplastic-Polyurethane.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-58130-Ester-Based-Thermoplastic-Polyurethane.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.23 g/cc	1.23 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	flex bar
	0.010 cm/cm	0.010 in/in	disk

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	47 - 53	47 - 53	ASTM D2240
	@Time 5.00 sec	@Time 0.00139 hour	
Tensile Strength	41.0 MPa	5950 psi	ASTM D412
Elongation at Break	530 %	530 %	ASTM D412/D638
100% Modulus	0.0110 GPa	1.60 ksi	ASTM D412
300% Modulus	0.0240 GPa	3.48 ksi	ASTM D412
Flexural Modulus	0.0900 GPa	13.1 ksi	ASTM D790
	0.103 GPa	15.0 ksi	ASTM D790
Tear Strength	42.1 kN/m	240 pli	Trouser; ASTM D470
Graves Tear Strength	138 kN/m	790 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	0.90	0.90	CS-17, 1000g; ASTM D3389 B
Compression Set	34 %	34 %	ASTM D395
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	
	43 %	43 %	ASTM D395
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Melting Point	218 °C	424 °F	DSC
Glass Transition Temp, Tg	-40.0 °C	-40.0 °F	DSC

Processing Properties	Metric	English	Comments
Rear Barrel Temperature	204 °C	399 °F	Injection
Middle Barrel Temperature	210 °C	410 °F	Injection
Front Barrel Temperature	218 °C	424 °F	Injection
Nozzle Temperature	223 °C	433 °F	Injection
Melt Temperature	223 °C	433 °F	Injection
Drying Temperature	104 °C	219 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Dew Point	-40.0 °C	-40.0 °F	
Injection Pressure	68.9 - 103 MPa	10000 - 15000 psi	Injection
Hold Pressure	34.5 - 68.9 MPa	5000 - 10000 psi	Injection
Back Pressure	>= 0.345 MPa	>= 50.0 psi	Injection
Screw Speed	60 - 100 rpm	60 - 100 rpm	Injection

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China