

## Lubrizol ESTANE® 58277 Ester Based Thermoplastic Polyurethane (European Grade)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

### Material Notes:

Description: Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs. Benefits of Estane® TPU: Outstanding Abrasion and Wear Resistance Excellent Low Temperature Flexibility Superior Toughness and Durability Ease of Processing and Manufacturing Flexibility Colorability and Paintability with no adhesion promoter Applications: Film & Sheet Fabric coating & melt coating Wire & Cable Hose, Tube & Profile Custom molding Custom compounding Automotive interior/chassis and exterior painted trim Specific Notes for this Material: Good chemical and hydrolysis resistance, clarity Information provided by Noveon, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-58277-Ester-Based-Thermoplastic-Polyurethane-European-Grade.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-58277-Ester-Based-Thermoplastic-Polyurethane-European-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.19 g/cc	1.19 g/cc	DIN 53479

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	93	93	DIN 53505
Hardness, Shore D	49	49	DIN 53505
Tensile Strength, Ultimate	47.0 MPa	6820 psi	DIN 53504
Elongation at Break	550 %	550 %	DIN 53504
50% Modulus	0.00890 GPa	1.29 ksi	DIN 53504
100% Modulus	0.0100 GPa	1.45 ksi	DIN 53504
300% Modulus	0.0174 GPa	2.52 ksi	DIN 53504
Tear Strength	100 kN/m	571 pli	DIN 53515
Abrasion	55	55	mm <sup>3</sup> ; DIN 53516
Compression Set	32 %	32 %	70 hrs./22°C; DIN 53517
	78 %	78 %	24 hrs./70°C; DIN 53517

Thermal Properties	Metric	English	Comments
Vicat Softening Point	74.0 °C	165 °F	A50; DIN 53460

Brittleness Temperature  
Thermal Properties

-70.0 °C  
Metric

-94.0 °F  
English

DIN 53546  
Comments

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China