

## Lubrizol ESTANE® 58680 Ester Based Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

### Material Notes:

Description: Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs. Benefits of Estane® TPU: Outstanding Abrasion and Wear Resistance Excellent Low Temperature Flexibility Superior Toughness and Durability Ease of Processing and Manufacturing Flexibility Colorability and Paintability with no adhesion promoter Applications: Film & Sheet Fabric coating & melt coating Wire & Cable Hose, Tube & Profile Custom molding Custom compounding Automotive interior/chassis and exterior painted trim Specific Notes for this Material: High elasticity and recovery Information provided by Noveon, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-58680-Ester-Based-Thermoplastic-Polyurethane.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-58680-Ester-Based-Thermoplastic-Polyurethane.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	74	74	ASTM D2240
Tensile Strength, Ultimate	43.4 MPa	6300 psi	ASTM D412/D638
Elongation at Break	660 %	660 %	ASTM D412/D638
Compression Set	21 %	21 %	ASTM D395
Tensile Set	5.0 %	5.0 %	ASTM D412/D638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	65.0 °C	149 °F	ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China