

Lubrizol ESTANE® 58866 Ether Based Thermoplastic Polyurethane (European Grade)

Category: Polymer, Thermoplastic, Elastomer, TPE, Polyurethane, TP, Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

Description: Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs.Benefits of Estane® TPU: Outstanding Abrasion and Wear ResistanceExcellent Low Temperature FlexibilitySuperior Toughness and DurabilityEase of Processing and Manufacturing FlexibilityColorability and Paintability with no adhesion promoterApplications: Film & SheetFabric coating & melt coatingWire & CableHose, Tube & ProfileCustom moldingCustom compoundingAutomotive interior/chassis and exterior painted trimInformation provided by Noveon, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-58866-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php

| Physical Properties | Metric | English | Comments |
|---------------------|-----------|-----------|-----------|
| Specific Gravity | 1.17 g/cc | 1.17 g/cc | DIN 53479 |

| Mechanical Properties | Metric | English | Comments |
|----------------------------|-------------|-----------|-----------------------------|
| Hardness, Shore A | 83 | 83 | DIN 53505 |
| Tensile Strength, Ultimate | 28.0 MPa | 4060 psi | DIN 53504 |
| Elongation at Break | 730 % | 730 % | DIN 53504 |
| 50% Modulus | 0.00400 GPa | 0.580 ksi | DIN 53504 |
| 100% Modulus | 0.00450 GPa | 0.653 ksi | DIN 53504 |
| 300% Modulus | 0.00690 GPa | 1.00 ksi | DIN 53504 |
| Tear Strength | 54.0 kN/m | 308 pli | DIN 53515 |
| Abrasion | 55 | 55 | mm ³ ; DIN 53516 |
| Compression Set | 24 % | 24 % | 70 hrs./22°C; DIN 53517 |
| | 70 % | 70 % | 24 hrs./70°C; DIN 53517 |

| Thermal Properties | Metric | English | Comments |
|-------------------------|----------|----------|----------------|
| Vicat Softening Point | 66.0 °C | 151 °F | A50; DIN 53460 |
| Brittleness Temperature | -70.0 °C | -94.0 °F | DIN 53546 |



Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China