

## Lubrizol ESTANE® 58881 Ether Based Thermoplastic Polyurethane (European Grade)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

### Material Notes:

Description: Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs. Benefits of Estane® TPU: Outstanding Abrasion and Wear Resistance Excellent Low Temperature Flexibility Superior Toughness and Durability Ease of Processing and Manufacturing Flexibility Colorability and Paintability with no adhesion promoter Applications: Film & Sheet Fabric coating & melt coating Wire & Cable Hose, Tube & Profile Custom molding Custom compounding Automotive interior/chassis and exterior painted trim Specific Notes for this Material: High resilient, low temperature flexibility Information provided by Noveon, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-58881-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-58881-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.10 g/cc	1.10 g/cc	ISO 2781

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	80	80	ISO 868
Tensile Strength, Ultimate	23.0 MPa	3340 psi	ISO 37
Elongation at Break	810 %	810 %	ISO 37
Tensile Modulus	0.0120 GPa	1.74 ksi	ISO 527
50% Modulus	0.00350 GPa	0.508 ksi	ISO 37
100% Modulus	0.00460 GPa	0.667 ksi	ISO 37
300% Modulus	0.00660 GPa	0.957 ksi	ISO 37
Rebound	56 %	56 %	ISO 4662
Tear Strength	35.0 kN/m	200 pli	with incision; ISO 34B
Abrasion	90	90	mm <sup>3</sup> ; ISO 4649
Compression Set	21 %	21 %	70 hrs./22°C; ISO 815
	65 %	65 %	24 hrs./70°C; ISO 815

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Vicat Softening Point Thermal Properties	56.0 °C Metric	133 °F English	A50: DIN 53460 Comments
Brittleness Temperature	-70.0 °C	-94.0 °F	DIN 53546

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China