

Lubrizol ESTANE® GP60DE Ester Based Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

Material Notes:

Estane® GP 60DE is an aromatic polyester-based thermoplastic polyurethane (TPU). Appearance: Translucent spherical pellets Uses: Injection molding parts Available in Europe Information provided by Lubrizol

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-GP60DE-Ester-Based-Thermoplastic-Polyurethane.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ISO 2781
Maximum Moisture Content	0.050	0.050	
Melt Flow	10 - 25 g/10 min @Load 8.70 kg, Temperature 210 °C	10 - 25 g/10 min @Load 19.2 lb, Temperature 410 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	60	60	ISO 868
Tensile Strength, Ultimate	45.0 MPa	6530 psi	ISO 37
Elongation at Break	560 %	560 %	ISO 37
Tensile Modulus	0.147 GPa	21.3 ksi	ISO 527
50% Modulus	0.0180 GPa	2.61 ksi	ISO 37
100% Modulus	0.0200 GPa	2.90 ksi	ISO 37
300% Modulus	0.0280 GPa	4.06 ksi	ISO 37
Rebound	34 %	34 %	ISO 4662
Tear Strength	169 kN/m	964 pli	with incision; ISO 34B
	195 kN/m	1110 pli	without incision; ISO 34B
Abrasion	49	49	mm³; ISO 4649
Compression Set	18 %	18 %	70 hrs./22°C; ISO 815
	26 %	26 %	24 hrs./70°C; ISO 815

Thermal Properties	Metric	English	Comments
Vicat Softening Point	154 °C	309 °F	A50; ISO 306

Processing Properties	Metric	English	Comments
Feed Temperature	40.0 °C	104 °F	Injection
Nozzle Temperature	205 - 215 °C	401 - 419 °F	Injection
Zone 1	195 - 205 °C	383 - 401 °F	Injection
Zone 2	210 - 220 °C	410 - 428 °F	Injection
Zone 3	210 - 220 °C	410 - 428 °F	Injection
Zone 4	215 - 225 °C	419 - 437 °F	Injection
Drying Temperature	105 °C	221 °F	
Dry Time	2.00 - 3.00 hour	2.00 - 3.00 hour	
Dew Point	-30.0 °C	-22.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China