

## Lubrizol ESTANE® GP85AB Ester Based Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

### Material Notes:

Type: Estane® GP 85AB is an aromatic polyester-based thermoplastic polyurethane (TPU). Appearance: Translucent spherical pellets  
Uses: Injection molding parts  
Information provided by Lubrizol.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-ESTANE-GP85AB-Ester-Based-Thermoplastic-Polyurethane.php](http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-GP85AB-Ester-Based-Thermoplastic-Polyurethane.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.20 g/cc	1.20 g/cc	ISO 2781
Maximum Moisture Content	0.050	0.050	
Melt Flow	20 - 40 g/10 min @Load 21.6 kg, Temperature 190 °C	20 - 40 g/10 min @Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	85	85	ISO 868
Hardness, Shore D	37	37	ISO 868
Tensile Strength, Ultimate	35.0 MPa	5080 psi	ISO 37
Elongation at Break	550 %	550 %	ISO 37
Tensile Modulus	0.0170 GPa	2.47 ksi	ISO 527
50% Modulus	0.00500 GPa	0.725 ksi	ISO 37
100% Modulus	0.00600 GPa	0.870 ksi	ISO 37
300% Modulus	0.0140 GPa	2.03 ksi	ISO 37
Rebound	40 %	40 %	ISO 4662
Tear Strength	75.0 kN/m	428 pli	with incision; ISO 34B
	112 kN/m	639 pli	without incision; ISO 34B
Abrasion	30	30	mm <sup>3</sup> ; ISO 4649
Compression Set	12 %	12 %	70 hrs./22°C; ISO 815
	28 %	28 %	24 hrs./70°C; ISO 815

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
<b>Processing Properties</b>	<b>Metric</b>	<b>English</b>	<b>Comments</b>
Feed Temperature	40.0 °C	104 °F	Injection
Nozzle Temperature	190 - 200 °C	374 - 392 °F	Injection
Zone 1	185 - 195 °C	365 - 383 °F	Injection
Zone 2	190 - 200 °C	374 - 392 °F	Injection
Zone 3	195 - 205 °C	383 - 401 °F	Injection
Zone 4	195 - 205 °C	383 - 401 °F	Injection
Drying Temperature	90.0 °C	194 °F	
Dry Time	2.00 - 3.00 hour	2.00 - 3.00 hour	
Dew Point	-30.0 °C	-22.0 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China