

Lubrizol ESTANE® GP98AE Ester Based Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Polyester Grade

Material Notes:

Type: Estane® GP 98AE is an aromatic polyester-based thermoplastic polyurethane (TPU). Appearance: Translucent spherical pellets
Uses: Injection molding parts
Available in Europe
Information provided by Lubrizol.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-GP98AE-Ester-Based-Thermoplastic-Polyurethane.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.25 g/cc	1.25 g/cc	ISO 2781
Maximum Moisture Content	0.050	0.050	
Melt Flow	20 - 35 g/10 min @Load 8.70 kg, Temperature 210 °C	20 - 35 g/10 min @Load 19.2 lb, Temperature 410 °F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	98	98	ISO 868
Hardness, Shore D	56	56	ISO 868
Tensile Strength, Ultimate	44.0 MPa	6380 psi	ISO 37
Elongation at Break	610 %	610 %	ISO 37
Tensile Modulus	0.118 GPa	17.1 ksi	ISO 527
50% Modulus	0.0160 GPa	2.32 ksi	ISO 37
100% Modulus	0.0170 GPa	2.47 ksi	ISO 37
300% Modulus	0.0250 GPa	3.63 ksi	ISO 37
Rebound	32 %	32 %	ISO 4662
Tear Strength	144 kN/m	822 pli	with incision; ISO 34B
	180 kN/m	1030 pli	without incision; ISO 34B
Abrasion	48	48	mm ³ ; ISO 4649
Compression Set	24 %	24 %	70 hrs./22°C; ISO 815
	40 %	40 %	24 hrs./70°C; ISO 815

Thermal Properties	Metric	English	Comments
--------------------	--------	---------	----------

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Feed Temperature	40.0 °C	104 °F	Injection
Nozzle Temperature	205 - 215 °C	401 - 419 °F	Injection
Zone 1	200 - 210 °C	392 - 410 °F	Injection
Zone 2	210 - 220 °C	410 - 428 °F	Injection
Zone 3	210 - 220 °C	410 - 428 °F	Injection
Zone 4	210 - 220 °C	410 - 428 °F	Injection
Drying Temperature	100 °C	212 °F	
Dry Time	2.00 - 3.00 hour	2.00 - 3.00 hour	
Dew Point	-30.0 °C	-22.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China