Lubrizol ESTANE® X1014 Ether Based Thermoplastic Polyurethane (European Grade)

Category : Polymer , Thermoplastic , Elastomer, TPE , Polyurethane, TP , Thermoplastic Polyurethane, Elastomer, Ether Grade

Material Notes:

Description: Estane® thermoplastic polyurethanes (TPUs) include elastomeric materials that bridge the gap between flexible rubber and rigid plastics. These materials offer toughness and durability in a flexible thermoplastic elastomer system that is easy to process in a wide range of equipment. The Estane® TPU portfolio of products offers high performance polyester - and polyether - based resins and compounds in a broad range of hardnesses to meet a variety of application needs.Benefits of Estane® TPU: Outstanding Abrasion and Wear ResistanceExcellent Low Temperature FlexibilitySuperior Toughness and DurabilityEase of Processing and Manufacturing Flexibility and Paintability with no adhesion promoterApplications: Film & SheetFabric coating & melt coatingWire & CableHose, Tube & ProfileCustom moldingCustom compoundingAutomotive interior/chassis and exterior painted trimInformation provided by Noveon, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-ESTANE-X1014-Ether-Based-Thermoplastic-Polyurethane-European-Grade.php

	1.18 g/cc Metric	1.18 g/cc	DIN 53479
Mechanical Properties	Metric		
	Metric		
		English	Comments
Hardness, Shore D	75	75	DIN 53505
Tensile Strength, Ultimate	41.0 MPa	5950 psi	DIN 53504
Elongation at Break	345 %	345 %	DIN 53504
50% Modulus	0.0254 GPa	3.68 ksi	DIN 53504
100% Modulus	0.0264 GPa	3.83 ksi	DIN 53504
300% Modulus	0.0299 GPa	4.34 ksi	DIN 53504
Flexural Stiffness	994.0 MPa	144200 psi	ASTM D747
Tear Strength	240 kN/m	1370 pli	DIN 53515
Abrasion	68	68	mm ³ ; DIN 53516

Descriptive Properties	Value	Comments
E-Modulus	1092 mm/min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com



Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China