

Lubrizol Estane® ETE 75DT3 Thermoplastic Polyurethane, Easy-to-Extrude

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyether Grade

Material Notes:

Type: Estane® ETE 75DT3 is an aromatic polyether-based thermoplastic polyurethane (TPU). Features: Hard TPU with wide extrusion processing window and melt stability, low temperature flexibility, high transparency and UV stability. Uses: Extrusion: Hose and Tube, Profile, Cable Jacket. Injection molding: Various. Available in Americas, Europe, Middle East, Africa, India and Asia. Information Provided by The Lubrizol Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lubrizol-Estane-ETE-75DT3-Thermoplastic-Polyurethane-Easy-to-Extrude.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.18 g/cc	1.18 g/cc	ASTM D792
Maximum Moisture Content	0.020	0.020	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	75	75	ASTM D2240
	@Time 5.00 sec	@Time 0.00139 hour	
Tensile Strength, Ultimate	40.7 MPa	5900 psi	ASTM D412
Elongation at Break	330 %	330 %	ASTM D412
100% Modulus	0.0220 GPa	3.19 ksi	ASTM D412
300% Modulus	0.0270 GPa	3.92 ksi	ASTM D412
Tear Strength	26.3 kN/m	150 pli	Trouser; ASTM D470
Graves Tear Strength	245 kN/m	1400 pli	Die C; ASTM D624
Taber Abrasion, mg/1000 Cycles	68	68	H-18 wheel; ASTM D3389
	@Load 1.00 kg	@Load 2.20 lb	

Thermal Properties	Metric	English	Comments
Melting Point	218 °C	424 °F	DSC
Glass Transition Temp, Tg	-10.0 °C	14.0 °F	DSC

Processing Properties	Metric	English	Comments
Zone 1	204 °C	399 °F	Extrusion
Zone 2	210 °C	410 °F	Extrusion

Processing Properties	Metric	English	Comments
Zone 4	216 °C	421 °F	Extrusion
Adapter Temperature	216 °C	421 °F	5, Extrusion
Die Temperature	218 °C	424 °F	6, Zone 1, Extrusion
	218 °C	424 °F	Zone 2, Extrusion
Drying Temperature	104 °C	219 °F	
Dry Time	2.00 - 4.00 hour	2.00 - 4.00 hour	
Dew Point	-40.0 °C	-40.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China