

## Lubrizol Estane® R195A Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyether Grade

**Material Notes:**

Type: Estane® R195A is a Shore 95A, polyether type thermoplastic polyurethane (TPU). FDA approved (21 CFR 177.2600, 177.1680). Uses: Injection Molding, Extrusion. Availability: Americas, Europe, Middle East, Africa, India and Asia. Information Provided by The Lubrizol Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-Estane-R195A-Thermoplastic-Polyurethane.php](http://www.lookpolymers.com/polymer_Lubrizol-Estane-R195A-Thermoplastic-Polyurethane.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.13 g/cc	1.13 g/cc	ASTM D792
Linear Mold Shrinkage	0.0070 cm/cm	0.0070 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	95	95	ASTM D2240
Hardness, Shore D	52	52	ASTM D2240
Tensile Strength, Ultimate	42.2 MPa	6120 psi	ASTM D412
Tensile Strength, Yield	11.3 MPa	1640 psi	at 100% elongation; ASTM D412
	19.6 MPa	2840 psi	at 300% elongation; ASTM D412
Elongation at Break	600 %	600 %	ASTM D412
Tear Strength	127 kN/m	728 pli	Die C; ASTM D624
Abrasion	25	25	mm <sup>3</sup> loss; ISO 4649
Compression Set	15 %	15 %	ASTM D395
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	
	45 %	45 %	ASTM D395
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	125 °C	257 °F	ASTM D1525

**Contact Songhan Plastic Technology Co.,Ltd.**

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**