

## Lubrizol Estane® S190A Thermoplastic Polyurethane

Category : Polymer , Thermoplastic , Polyurethane, TP , Thermoplastic Polyurethane (TPUR), Polyester Grade

### Material Notes:

Type: Estane® S190A is a Shore 92A, polyester based thermoplastic polyurethane (TPU). FDA approved (21 CFR 177.2600, 177.1680). Uses: Injection Molding. Availability: Asia Information Provided by The Lubrizol Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lubrizol-Estane-S190A-Thermoplastic-Polyurethane.php](http://www.lookpolymers.com/polymer_Lubrizol-Estane-S190A-Thermoplastic-Polyurethane.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Linear Mold Shrinkage	0.0090 cm/cm	0.0090 in/in	ASTM D955

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	92	92	ASTM D2240
Hardness, Shore D	48	48	ASTM D2240
Tensile Strength, Ultimate	49.0 MPa	7110 psi	ASTM D412
Tensile Strength, Yield	9.32 MPa	1350 psi	at 100% elongation; ASTM D412
	18.6 MPa	2700 psi	at 300% elongation; ASTM D412
Elongation at Break	650 %	650 %	ASTM D412
Tear Strength	137 kN/m	784 pli	Die C; ASTM D624
Abrasion	30	30	mm <sup>3</sup> loss; ISO 4649
Compression Set	15 %	15 %	ASTM D395
	@Temperature 23.0 °C, Time 79200 sec	@Temperature 73.4 °F, Time 22.0 hour	
	40 %	40 %	ASTM D395
	@Temperature 70.0 °C, Time 79200 sec	@Temperature 158 °F, Time 22.0 hour	

Thermal Properties	Metric	English	Comments
Vicat Softening Point	110 °C	230 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Feed Temperature	185 - 195 °C	365 - 383 °F	

Processing Properties	190 - 205 °C Metric	374 - 401 °F English	Comments
Mold Temperature	10.0 - 40.0 °C	50.0 - 104 °F	
Drying Temperature	70.0 - 80.0 °C	158 - 176 °F	
Dry Time	4.00 - 5.00 hour	4.00 - 5.00 hour	
Injection Pressure	8.27 - 13.8 MPa	1200 - 2000 psi	
Hold Pressure	8.27 - 12.4 MPa	1200 - 1800 psi	
Back Pressure	0.207 - 0.552 MPa	30.0 - 80.0 psi	
Cycle Time - Injection	25 - 35 sec	25 - 35 sec	
Screw Speed	180 - 220 rpm	180 - 220 rpm	

Descriptive Properties	Value	Comments
Injection time (s)	12-18	
Metering Zone	185-200°C	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China