

## Lucas-Milhaupt 60 Sn-40 Pb Tin/ Silver Solder

Category: Metal, Nonferrous Metal, Solder/Braze Alloy, Tin Alloy

## **Material Notes:**

Applications and Characteristics: Although widely used in electronics for both manual and automatic soldering applications, it is also used in general purpose applications where fast alloy flow is desired. This alloy offers good corrosion resistance properties and is generally used where temperature requirements are critical. Joint clearances of 0.1 to 0.15mm (.003 to .005 in) are optimum, but larger variations can still produce sound joints. Flux is required and proper selection will depend upon base metals to be joined. Specifications: This alloy conforms to the following specification: ASTM 60B, B32 SN60 Information provided by Lucas-Milhaupt, Inc.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Lucas-Milhaupt-60-Sn-40-Pb-Tin-Silver-Solder.php

Physical Properties	Metric	English	Comments
Specific Gravity	8.67 g/cc	8.67 g/cc	

Thermal Properties	Metric	English	Comments
Melting Point	182 - 191 °C	360 - 375 °F	
Solidus	182 °C	360 °F	Melting Point
Liquidus	191 °C	375 °F	Flow Point

Component Elements Properties	Metric	English	Comments	
Lead, Pb	39.5 - 40.5 %	39.5 - 40.5 %		
Tin, Sn	59.5 - 60.5 %	59.5 - 60.5 %		

Descriptive Properties	Value	Comments
Color	White	

## Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China