

Lucent Polymers ABS-305LG Acrylonitrile Butadiene Styrene, General Purpose, Low Gloss

Category : Polymer , Thermoplastic , ABS Polymer

Material Notes:

Add "R" for Added ReleaseAdd "U" for UV StabilizerInformation provided by Lucent Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucent-Polymers-ABS-305LG-Acrylonitrile-Butadiene-Styrene-General-Purpose-Low-Gloss.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0060 cm/cm @Thickness 3.17 mm	0.0060 in/in @Thickness 0.125 in	1/8" Section
Melt Flow	5.0 g/10 min	5.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	42.07 MPa	6102 psi	ASTM D638
Elongation at Yield	>= 10 %	>= 10 %	ASTM D638
Flexural Strength	74.48 MPa	10800 psi	ASTM D790
Flexural Modulus	2.2069 GPa	320.08 ksi	ASTM D790
Izod Impact, Notched	1.602 J/cm @Thickness 3.17 mm, Temperature 22.8 Â°C	3.001 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	87.78 Â°C	190.0 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China