

## Lucent Polymers CPP-210 Polypropylene, 10% Calcium Carbonate Filled, Impact Modified

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 10% Calcium Carbonate (CaCO3) Filler

### Material Notes:

Melt Flow Adjustable for Application Add "U" for UV Stabilized Add "H" for Heat Stabilized Information provided by Lucent Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucent-Polymers-CPP-210-Polypropylene-10-Calcium-Carbonate-Filled-Impact-Modified.php](http://www.lookpolymers.com/polymer_Lucent-Polymers-CPP-210-Polypropylene-10-Calcium-Carbonate-Filled-Impact-Modified.php)

Physical Properties	Metric	English	Comments
Specific Gravity	0.980 g/cc	0.980 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.014 cm/cm @Thickness 3.17 mm	0.014 in/in @Thickness 0.125 in	1/8" Section

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.9 MPa	3900 psi	ASTM D638
Elongation at Break	>= 10 %	>= 10 %	ASTM D638
Flexural Strength	43.45 MPa	6302 psi	ASTM D790
Flexural Modulus	1.310 GPa	190.0 ksi	ASTM D790
Izod Impact, Notched	0.961 J/cm @Thickness 3.17 mm	1.80 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	57.22 Â°C	135.0 Â°F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China