

Lucent Polymers GPCB-330 Polycarbonate+PBT, 30% Glass Fiber Reinforced, Impact Resistant

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Glass Filled , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Add "R" for Added ReleaseAdd "U" for UV StabilizerInformation provided by Lucent Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucent-Polymers-GPCB-330-PolycarbonatePBT-30-Glass-Fiber-Reinforced-Impact-Resistant.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.44 g/cc	1.44 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0040 cm/cm @Thickness 3.17 mm	0.0040 in/in @Thickness 0.125 in	1/8" Section
Melt Flow	8.0 g/10 min @Load 5.00 kg, Temperature 260 Â°C	8.0 g/10 min @Load 11.0 lb, Temperature 500 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	91.03 MPa	13200 psi	ASTM D638
Elongation at Break	>= 3.0 %	>= 3.0 %	ASTM D638
Flexural Strength	137.93 MPa	20005 psi	ASTM D790
Flexural Modulus	5.241 GPa	760.2 ksi	ASTM D790
Izod Impact, Notched	1.602 J/cm @Thickness 3.17 mm, Temperature 22.8 Â°C	3.001 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	148.89 Â°C	300.00 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China