

## Lucent Polymers GPP-240 Homopolymer Polypropylene, 40% Glass Fiber Reinforced, Chemically Coupled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 40% Glass Fiber Filler

### Material Notes:

Melt Flow Adjustable for ApplicationAdd "U" for UV StabilizedAdd "H" for Heat StabilizedInformation provided by Lucent Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucent-Polymers-GPP-240-Homopolymer-Polypropylene-40-Glass-Fiber-Reinforced-Chemically-Coupled.php](http://www.lookpolymers.com/polymer_Lucent-Polymers-GPP-240-Homopolymer-Polypropylene-40-Glass-Fiber-Reinforced-Chemically-Coupled.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0030 cm/cm @Thickness 3.17 mm	0.0030 in/in @Thickness 0.125 in	1/8" Section

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	86.21 MPa	12500 psi	ASTM D638
Elongation at Break	3.0 %	3.0 %	ASTM D638
Flexural Strength	120.69 MPa	17505 psi	ASTM D790
Flexural Modulus	6.2069 GPa	900.24 ksi	ASTM D790
Izod Impact, Notched	1.17 J/cm @Thickness 3.17 mm	2.20 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	137.78 Å°C	280.00 Å°F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China