

## Lucent Polymers PC/PBT-1430U Polycarbonate+PBT, Superior Weatherability, Injection Grade

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

### Material Notes:

Add "R" for Added ReleaseAdd "U" for UV StabilizerInformation provided by Lucent Polymers, Inc.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucent-Polymers-PCPBT-1430U-PolycarbonatePBT-Superior-Weatherability-Injection-Grade.php](http://www.lookpolymers.com/polymer_Lucent-Polymers-PCPBT-1430U-PolycarbonatePBT-Superior-Weatherability-Injection-Grade.php)

Physical Properties	Metric	English	Comments
Specific Gravity	1.21 g/cc	1.21 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.0080 cm/cm @Thickness 3.17 mm	0.0080 in/in @Thickness 0.125 in	1/8" Section
Melt Flow	30 g/10 min @Load 5.00 kg, Temperature 260 Â°C	30 g/10 min @Load 11.0 lb, Temperature 500 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	62.07 MPa	9003 psi	ASTM D638
Elongation at Break	>= 110 %	>= 110 %	ASTM D638
Flexural Strength	95.17 MPa	13800 psi	ASTM D790
Flexural Modulus	2.469 GPa	358.1 ksi	ASTM D790
Izod Impact, Notched	7.48 J/cm @Thickness 3.17 mm, Temperature 22.8 Â°C	14.0 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	87.78 Â°C	190.0 Â°F	ASTM D648

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China