

Lucent Polymers PC/PBT-1550 Polycarbonate+PBT, Improved Impact Resistance, Injection Grade

Category : Polymer , Thermoplastic , Polycarbonate (PC) , Polycarbonate/Polybutylene Terephthalate (PBT) Blend, Unreinforced , Polyester, TP , Polybutylene Terephthalate (PBT)

Material Notes:

Add "R" for Added ReleaseAdd "U" for UV StabilizerInformation provided by Lucent Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucent-Polymers-PCPBT-1550-PolycarbonatePBT-Improved-Impact-Resistance-Injection-Grade.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.24 g/cc	1.24 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.014 cm/cm @Thickness 3.17 mm	0.014 in/in @Thickness 0.125 in	1/8" Section
Melt Flow	50 g/10 min @Load 5.00 kg, Temperature 260 Â°C	50 g/10 min @Load 11.0 lb, Temperature 500 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	46.9 MPa	6800 psi	ASTM D638
Elongation at Break	>= 128 %	>= 128 %	ASTM D638
Flexural Strength	75.86 MPa	11000 psi	ASTM D790
Flexural Modulus	2.00 GPa	290 ksi	ASTM D790
Izod Impact, Notched	4.27 J/cm @Thickness 3.17 mm, Temperature -30.0 Â°C	8.00 ft-lb/in @Thickness 0.125 in, Temperature -22.0 Â°F	ASTM D256
	8.01 J/cm @Thickness 3.17 mm, Temperature 22.8 Â°C	15.0 ft-lb/in @Thickness 0.125 in, Temperature 73.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	86.67 Â°C	188.0 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China