

Lucent Polymers PPC-220 Polypropylene, Impact Modified

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

Add "U" for UV Stabilized Add "H" for Heat Stabilized Information provided by Lucent Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucent-Polymers-PPC-220-Polypropylene-Impact-Modified.php

Physical Properties	Metric	English	Comments
Specific Gravity	0.910 g/cc	0.910 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.016 cm/cm @Thickness 3.17 mm	0.016 in/in @Thickness 0.125 in	1/8" Section
Melt Flow	20 g/10 min @Load 2.16 kg, Temperature 230 Â°C	20 g/10 min @Load 4.76 lb, Temperature 446 Â°F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	33.17 MPa	4811 psi	ASTM D638
Elongation at Break	>= 10 %	>= 10 %	ASTM D638
Flexural Strength	37.93 MPa	5501 psi	ASTM D790
Flexural Modulus	1.034 GPa	150.0 ksi	ASTM D790
Izod Impact, Notched	0.961 J/cm @Thickness 3.17 mm	1.80 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	51.67 Â°C	125.0 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China