

Lucent Polymers TPP-130 Polypropylene, Homopolymer, 30% Talc Filled

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene with 30% Talc Filler

Material Notes:

Melt Flow Adjustable for Application Add "U" for UV Stabilized Add "H" for Heat Stabilized Information provided by Lucent Polymers, Inc.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucent-Polymers-TPP-130-Polypropylene-Homopolymer-30-Talc-Filled.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.14 g/cc	1.14 g/cc	ASTM D792
Linear Mold Shrinkage, Flow	0.012 cm/cm @Thickness 3.17 mm	0.012 in/in @Thickness 0.125 in	1/8" Section

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	31.72 MPa	4601 psi	ASTM D638
Elongation at Break	>= 10 %	>= 10 %	ASTM D638
Flexural Strength	52.41 MPa	7601 psi	ASTM D790
Flexural Modulus	3.034 GPa	440.1 ksi	ASTM D790
Izod Impact, Notched	0.267 J/cm @Thickness 3.17 mm	0.500 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	79.44 Â°C	175.0 Â°F	ASTM D648

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China