

Lucite International Diakon® CLG902LX Acrylic Polymer

Category : Polymer , Thermoplastic , Acrylic (PMMA) , Acrylic, General Purpose, Molded

Material Notes:

Information provided by Lucite International

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lucite-International-Diakon-CLG902LX-Acrylic-Polymer.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	ISO 1183
Water Absorption	0.30 %	0.30 %	ISO 62
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	
Melt Flow	7.3 g/10 min	7.3 g/10 min	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	92	92	ISO 2039-2
Ball Indentation Hardness	180 MPa	26100 psi	ISO 2039-1
Tensile Strength	80.0 MPa	11600 psi	ISO 527
Elongation at Break	5.0 %	5.0 %	ISO 527
Flexural Strength	110 MPa	16000 psi	ISO 178
Flexural Modulus	3.00 GPa	435 ksi	ISO 178
Izod Impact, Notched (ISO)	1.80 kJ/m ²	0.857 ft-lb/in ²	ISO 180/1A
Charpy Impact, Notched	0.200 J/cm ²	0.952 ft-lb/in ²	ISO 179/1eA
	2.00 J/cm ²	9.52 ft-lb/in ²	ISO 179/1eU

Thermal Properties	Metric	English	Comments
CTE, linear	71.0 Åµm/m-Å°C	39.4 Åµin/in-Å°F	ASTM E831
Vicat Softening Point	102 Å°C	216 Å°F	ISO 306B
	108 Å°C	226 Å°F	ISO 306A
Heat Distortion Temperature	97.0 Å°C	207 Å°F	ISO 75A
	100 Å°C	212 Å°F	ISO 75B
Flammability, UL94	HB	HB	

Thermal Properties	Metric	English	Comments
Optical Properties	Metric	English	Comments
Refractive Index	1.49	1.49	ISO 489
Haze	0.40 %	0.40 %	ASTM D1003
Transmission, Visible	92 %	92 %	ASTM D1003

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China