

## Lucobit Lucofin® 1414-t3 Polyolefin TPO Granules, Silk Grey

Category : Polymer , Thermoplastic , Polyolefin

**Material Notes:**

Lucofin are colored, highly stabilized polyolefin-based TPO granules. The t3 series is distinguished by good tenacity, high biaxial extensibility and flexibility outstanding breaking strength, and flexibility and resistance to weathering even at low temperatures. Applications:• Colored roof sheeting• Sealing sheeting• Construction profiles This product is provided with special halogen free fire retardants in order to pass test method 3 of European standard EN 1187. Information provided by Lucobit AG

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Lucobit-Lucofin-1414-t3-Polyolefin-TPO-Granules-Silk-Grey.php](http://www.lookpolymers.com/polymer_Lucobit-Lucofin-1414-t3-Polyolefin-TPO-Granules-Silk-Grey.php)

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in <sup>3</sup>	ISO 1183
Melt Flow	8.0 g/10 min @Load 2.16 kg, Temperature 190 °C	8.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	95	95	ISO 868

Thermal Properties	Metric	English	Comments
Minimum Service Temperature, Air	<= -40.0 °C	<= -40.0 °F	Low Temperature Flexural Test; EN 495-5

Processing Properties	Metric	English	Comments
Processing Temperature	150 - 200 °C	302 - 392 °F	Profiles
	160 - 230 °C	320 - 446 °F	Membranes
	160 - 270 °C	320 - 518 °F	Coatings
Melt Temperature	160 - 220 °C	320 - 428 °F	
Mold Temperature	10.0 - 40.0 °C	50.0 - 104 °F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China