

Lushan L-5R (HC) Polyethylene Copolymer Adhesive for Steel Pipe Coating

Category : Polymer , Thermoplastic , Polyethylene (PE)

Material Notes:

Copolymer adhesive resin Lushan L-5R series is maleic anhydride grafted polyethylene which could be in granule or powder form. It was developed by Lushan with independent patent technologies and proved with excellent performance in the widely applications of pipeline projects both in China and international market. The purpose of the adhesive is to bond the epoxy layer to the top coat. Copolymer adhesive resin Lushan L-5R series in mainly used as adhesive layer in 3 layers polyethylene system (3LPE) for steel pipe against corrosion coating system in oil and gas pipeline and high pressure water pipeline. Copolymer adhesive resin Lushan L-5R series has good properties such as high bonding strength, long-term stability, wide compatibility, easy processing, etc. Copolymer adhesive resin Lushan L-5R series designed to meet with requirements of the following National and international standards, under the condition that appropriate industrial processing method are applied under a continuous quality control system and when used in combination copolymer adhesive resin Lushan L-5R& polyethylene compound top coats EJ-1 and compatible powder epoxy. Information provided by Lushan

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lushan-L-5R-HC-Polyethylene-Copolymer-Adhesive-for-Steel-Pipe-Coating.php

Physical Properties	Metric	English	Comments
Density	0.938 g/cc	0.0339 lb/in ³	ASTM D792
Melt Index of Compound	3.8 g/10 min	3.8 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	26.0 MPa	3770 psi	ASTM D638
Elongation at Break	960 %	960 %	ASTM D638
Peel Strength	>= 80.0 kN/m	>= 456 pli	80+5 ^o C; ISO 21809-1
	>= 120 kN/m	>= 685 pli	60+5 ^o C; ISO 21809-1
	>= 150 kN/m	>= 856 pli	50+5 ^o C; ISO 21809-1
	>= 180 kN/m	>= 1030 pli	20+5 ^o C; ISO 21809-1

Thermal Properties	Metric	English	Comments
Melting Point	131 ^o C	268 ^o F	ASTM D2117
Maximum Service Temperature, Air	80.0 ^o C	176 ^o F	
Vicat Softening Point	118 ^o C	244 ^o F	ASTM D1525
Minimum Service Temperature, Air	-40.0 ^o C	-40.0 ^o F	
Brittleness Temperature	-70.0 ^o C	-94.0 ^o F	ASTM D746

Descriptive Properties	Value	Comments
Appearance	granule	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China