

Lushan PP+GF30%+4% PR-3 Maleic Anhydride Grafted Polypropylene

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

Maleic anhydride grafted polypropylene (PP-a-MAH) Lushan series is evaluated as compatibilizer/coupling agent which is used to fill or reinforced polypropylene. As the coupling agent, PP-g-MAH can significantly improve the filled or enhanced PP's mechanical properties and heat resistance. As the same time, the introduction of polypropylene molecular chain polar groups could significantly improve PP's shading ability. Maleic Anhydride Grafted Polypropylene Usage:As compatibilizer/ coupling agent for polypropylene filled with glass fiber or mineral: maleic anhydride grafted polypropylene as a high polarity. As long as adding a small amount (4%), it can significantly improve interface bonding strength between PP and the glass fiber, talc, mica and other inorganic fillers. Modified polypropylene's tensile strength, bending strength and impact strength have been improved significantly.As compatibilizer/coupling agent for PA/PP, PA/PE alloy: to improve the processing of nylon, impact resistance, lower water absorption and products dimensional stability.Improve coating and painting/shagging properties for polypropylene.Information provided by Lushan

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lushan-PPGF304-PR-3-Maleic-Anhydride-Grafted-Polypropylene.php

Mechanical Properties	Metric	English	Comments
Tensile Strength at Break	80.0 MPa	11600 psi	
Flexural Strength	130 MPa	18900 psi	
Izod Impact, Notched (ISO)	12.0 kJ/m ²	5.71 ft-lb/in ²	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China