

Lushan PR296B Adhesive Resin for Aluminum Plastic Composite Pipe

Category: Polymer, Adhesive, Thermoplastic, Polypropylene (PP)

Material Notes:

Adhesive resin Lushan series for aluminum-plastic composite pipe is maleic grafted polyethylene used for PE-AL-PE, PEX-AL-PEX and PERT-AL-PERT composite pipes. Lushan adhesive resin could provides innovative solutions for plumbing and heating pipe systems including applications of domestic water piping, under-floor heating, radiator connections and wall, cooling and heating installations, district heating and industrial piping, etc. PPR pipe adhesive resin Lushan series is maleic grafted polypropylene used for PPR piping system. Lushan makes its adhesive resin to be possible to combine the advantages of materials and polymers in the multi-layer aluminum plastic composite structures. The high mechanical and thermal cycle resistance of Lushan adhesive resin provide an excellent bonding effect over a wide temperature range. Applications: PP-R PipeCo-Extrusion LaminatingInformation provided by Lushan

Order this product through the following link:

http://www.lookpolymers.com/polymer_Lushan-PR296B-Adhesive-Resin-for-Aluminum-Plastic-Composite-Pipe.php

| Physical Properties | Metric | English | Comments |
|------------------------|---------------|---------------|-------------------------|
| Density | 0.900 g/cc | 0.0325 lb/in³ | ASTM D1505 |
| Melt Index of Compound | 5.0 g/10 min | 5.0 g/10 min | 190°C/230°C; ASTM D1238 |
| | @Load 2.16 kg | @Load 4.76 lb | |

| Mechanical Properties | Metric | English | Comments |
|-----------------------|--------|---------|-----------|
| Elongation at Break | 300 % | 300 % | ASTM D638 |

| Thermal Properties | Metric | English | Comments |
|-----------------------|--------|---------|------------|
| Melting Point | 155 °C | 311 °F | ASTM D2117 |
| Vicat Softening Point | 100 °C | 212 °F | ASTM D1525 |

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China