

LyondellBasell Adsylâ, ¢ 5 C 30 F Polyolefin

Category : Polymer , Film , Thermoplastic , Polyolefin , Polyolefin, Film Grade , Polyolefin, Film Grade (Polyolefin)

Material Notes:

Description: Adsylâ,,¢ 5 C 30 F is a new thermoplastic polyolefin which has been designed as a BOPP sealing layer material with exceptionally low sealing temperature. It features a high clarity and gloss, a low haze, a wide hot-tack range and a Seal-Initiation Temperature (SIT) of 106ŰC measured on 30 ŵm film. It does not contain any slip nor anti-blocking agents and is therefore suitable for the production of metallized film. Adsylâ,¢ 5 C 30 F can be processed on both stenter and double bubble equipment. The composition of the product complies with FDA norms and with regulations in force in major European concerning food contact applications.Information provided by Basell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Adsyl-5-C-30-F-Polyolefin.php

| Physical Properties | Metric | English | Comments | |
|---------------------|--------------------------------------|--------------------------------------|-----------------------|--|
| Density | 0.890 g/cc | 0.0322 lb/in³ | ISO 1183 | |
| Melt Flow | 5.5 g/10 min | 5.5 g/10 min | | |
| | @Load 2.16 kg, Temperature 230 °C | @Load 4.76 lb, Temperature 446 °F | Condition L; ISO 1133 | |

| Mechanical Properties | Metric | English | Comments |
|--|----------|----------|-----------------------|
| Heat Seal Strength Initiation Temperature | 106.1 °C | 223.0 °F | 1.2 mil |
| | | | |
| Thermal Properties | Metric | English | Comments |
| Melting Point | 135 °C | 275 °F | MTM 15902 |
| | | | |
| Optical Properties | Metric | English | Comments |
| Haze | 1.5 % | 1.5 % | MTM 17031, 50 µm film |

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com Email : sales@lookpolymers.com Tel : +86 021-51131842 Mobile : +86 13061808058 Skype : lookpolymers Address : United North Road 215,Fengxian District, Shanghai City,China