

LyondellBasell Alathon® M5562 High Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Injection Molded

Material Notes:

ApplicationsALATHON M 5562 is a copolymer with medium molecular weight distribution. This resin provides moderate stiffness, toughness and stress crack resistance. Typical applications include nozzle valves and specialty injection molded parts.**Regulatory Status**M 5562 meets the requirements of Food and Drug Administration regulation, 21 CFR 177.1520. This regulation allows the use of this olefin polymer in "articles or components of articles intended for use in contact with food." Specific limitations or conditions of use may apply. Contact your Equistar sales representative for more information. **Processing Techniques**Specific recommendations for processing M 5562 can only be made when the processing conditions, equipment and end use are known. For further suggestions, please contact your Equistar sales representative.This product is from the former Equistar product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Alathon-M5562-High-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.955 g/cc	0.0345 lb/in ³	ASTM D1505
Melt Flow	6.0 g/10 min	6.0 g/10 min	ASTM D1238
Spiral Flow	31.5 cm	12.4 in	Measures the number on inches of flow produced when molten resin is injected into a long, spiral channel (0.625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440° F; Equistar

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	68	68	ASTM D2240
Tensile Strength at Break	18.2 MPa	2640 psi	ASTM D638
Tensile Strength, Yield	29.5 MPa	4280 psi	Crosshead speed - 2"min.; ASTM D638
Elongation at Yield	7.0 %	7.0 %	Crosshead speed - 2"min.; ASTM D638
1% Secant Modulus	1320 MPa	191000 psi	Crosshead speed - 0.5" min; ASTM D790
2% Secant Modulus	1.08 GPa	157 ksi	Crosshead speed - 0.5" min; ASTM D790

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	60.0 Â°C	140 Â°F	ASTM D648
Vicat Softening Point	125 Â°C	257 Â°F	ASTM D1525

Brittleness Temperature
Thermal Properties

≤ -76.0 °C
Metric

≤ -105 °F
English

F₅₀; ASTM D746
Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China