

## LyondellBasell Lupolen® 5261 Z HDPE, Blow Molding Grade

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

### Material Notes:

Relatively high viscosity blow molding grade for rigid, stackable and highly shock resistant containers for packaging all types of hazardous materials such as flammable, corrosive, poisonous and surface-active chemicals. Data was collected by ISO methods and originally provided by BASF. The Lupolen® product line is now produced by Basell.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_LyondellBasell-Lupolen-5261-Z-HDPE-Blow-Molding-Grade.php](http://www.lookpolymers.com/polymer_LyondellBasell-Lupolen-5261-Z-HDPE-Blow-Molding-Grade.php)

Physical Properties	Metric	English	Comments
Density	0.954 g/cc	0.0345 lb/in <sup>3</sup>	
Water Absorption	0.010 %	0.010 %	
Moisture Absorption at Equilibrium	0.010 %	0.010 %	
High Load Melt Index	0.10 g/10 min	0.10 g/10 min	
	@Load 21.6 kg, Temperature 190 °C	@Load 47.6 lb, Temperature 374 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	27.0 MPa	3920 psi	
Elongation at Break	>= 50 %	>= 50 %	
Elongation at Yield	9.0 %	9.0 %	
Tensile Modulus	1.20 GPa	174 ksi	
Tensile Impact Strength	300 kJ/m <sup>2</sup>	143 ft-lb/in <sup>2</sup>	
Tensile Creep Modulus, 1 hour	430 MPa	62400 psi	
Tensile Creep Modulus, 1000 hours	290 MPa	42100 psi	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	145 µm/m-°C	80.6 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Melting Point	134 °C	273 °F	
Deflection Temperature at 0.46 MPa (66 psi)	75.0 °C	167 °F	
Deflection Temperature at 1.8 MPa	44.0 °C	111 °F	

<small>(264 psi)</small> Thermal Properties	Metric	English	Comments
Vicat Softening Point	80.0 Å°C	176 Å°F	
Flammability, UL94	HB @Thickness 0.400 mm	HB @Thickness 0.0157 in	
Oxygen Index	17 %	17 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	
Dielectric Constant	2.4 @Frequency 100 Hz	2.4 @Frequency 100 Hz	
	2.4 @Frequency 1e+6 Hz	2.4 @Frequency 1e+6 Hz	
Dielectric Strength	150 kV/mm	3810 kV/in	
Dissipation Factor	0.00020 @Frequency 100 Hz	0.00020 @Frequency 100 Hz	
	0.00020 @Frequency 1e+6 Hz	0.00020 @Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China