

LyondellBasell Lupolen® V 2920 K Ethylene Vinyl Acetate, Injection Molding Grade

Category : Polymer , Thermoplastic , Ethylene Vinyl Acetate , Ethylene Vinyl Acetate; Molded/Extruded

Material Notes:

Injection moldingsData was collected by ISO methods and originally provided by BASF. The Lupolen® product line is now produced by Basell.

Order this product through the following link:

http://www.lookpolymers.com/polymer_LyondellBasell-Lupolen-V-2920-K-Ethylene-Vinyl-Acetate-Injection-Molding-Grade.php

Physical Properties	Metric	English	Comments
Density	0.928 g/cc	0.0335 lb/in ³	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	8.00 MPa	1160 psi	
Elongation at Break	>= 50 %	>= 50 %	
Tensile Modulus	0.105 GPa	15.2 ksi	

Thermal Properties	Metric	English	Comments
Melting Point	97.0 Â°C	207 Â°F	
Flammability, UL94	HB @Thickness 3.20 mm	HB @Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	>= 1.00e+15 ohm-cm	>= 1.00e+15 ohm-cm	
Dielectric Constant	2.5 @Frequency 100 Hz	2.5 @Frequency 100 Hz	
Dissipation Factor	0.013 @Frequency 100 Hz	0.013 @Frequency 100 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China